

SECTION GUIDE

RELEASE FILMS

Name	Description	Maximum use temperature	Elongation at break	Colour
Wrightlon® 3700	Polyolefin	121°C	500 %	Blue
Wrightlon® 3900	Polyolefin	157°C	500 %	Red / Blue
Wrightlon® 4600	PMP	193°C	250 %	Blue / Clear
Wrightlon® 5200	ETFE	260°C	350 %	Blue / Red / Clear
A4000	FEP	260°C	300 %	Clear/Red/Violet/White
A4000 LFST	FEP	260°C	300 %	Various
RF 242	ETFE	220°C	350 %	Blue / Red
RF 260	FEP	260°C	300 %	Clear / Red
Dahlar® Release Bag 125	Polyolefin, multi-layer	140°C	400 %	Green
Airtech MR1 / MR2	Fluoropolymer	315°C	400 %	Red / Beige
TF125	Fluoropolymer	260°C	225 %	Beige
Thermalimide E RCBS	Polyimide	405°C	85 %	Amber
Available perforations	-	-	-	
Resin Compatibility				
Commonly Used Sizes	-	-	-	-