

## SECTION GUIDE

## RELEASE FABRICS / PEEL PLIES

Name	Material type	Release coating	Maximum use temperature	Weight	Colour
60B	Nylon	-	205°C	60 g / m <sup>2</sup>	White
60BR	Nylon	Silicone	205°C	60 g / m <sup>2</sup>	Orange
80A	Nylon	-	205°C	80 g / m <sup>2</sup>	White
80AR	Nylon	Silicone	205°C	80 g / m <sup>2</sup>	Orange
Release Ply A	Nylon	-	232°C	80 g / m <sup>2</sup>	Off-white
Release Ply Super A	Nylon	-	232°C	139 g / m <sup>2</sup>	White
Stitch Ply A	Nylon	-	232°C	88 g / m <sup>2</sup>	White
Release Ply B	Nylon	-	232°C	62 g / m <sup>2</sup>	White
Release Ply C	Polyester	-	204°C	64 g / m <sup>2</sup>	White
Release Ply F	Polyester	-	204°C	95 g / m <sup>2</sup>	White
Release Ply Super F	Polyester	-	204°C	114 g / m <sup>2</sup>	White
Release Ply G	Polyester	-	204°C	92 g / m <sup>2</sup>	White
Stitch Ply G	Polyester	-	204°C	92 g / m <sup>2</sup>	White
Ultra Ply 22 T	Polyester	-	204°C	95 g / m <sup>2</sup>	White
Bleeder Lease® A	Nylon	Silicone	232°C	80 g / m <sup>2</sup>	Green
Bleeder Lease® B	Nylon	Silicone	232°C	62 g / m <sup>2</sup>	Green
Bleeder Lease® C	Fibreglass	Silicone	427°C	299 g / m <sup>2</sup>	Green
Bleeder Lease® E	Fibreglass	Silicone	427°C	126 g / m <sup>2</sup>	Green
Bleeder Lease® G	Polyester	Silicone	204°C	83 g / m <sup>2</sup>	Green
Superlease Blue	Nylon	Silicone	232°C	62 g / m <sup>2</sup>	Blue
Econostitch®	Nylon	-	190°C	88 g / m <sup>2</sup>	White
Econostitch® G	Polyester	-	190°C	85 g / m <sup>2</sup>	White
Econoply E	Polyester	-	149°C	95 g / m <sup>2</sup>	White
Econoply J	Polyester	-	121°C	54 g / m <sup>2</sup>	White
Econolease	Nylon	Silicone	204°C	61 g / m <sup>2</sup>	Light blue
TFG 075	PTFE Coated Fibreglass	-	260°C		Brown
TFG 125	PTFE Coated Fibreglass	-	260°C		Brown
TFG 250	PTFE Coated Fibreglass	-	260°C		Brown
TFG075P&TFGS075P	PTFE Coated Fibreglass	-	260°C		Brown
TFG 125TR	PTFE Coated Fibreglass	-	260°C		Brown
TFG 125P	PTFE Coated Fibreglass	-	260°C		Brown
TFG 250P	PTFE Coated Fibreglass	-	260°C		Brown
Release Ease® 234 TFP	Fibreglass	PTFE	288°C	-	Brown

## SECTION GUIDE

## RELEASE FABRICS / PEEL PLIES

Name	Material type	Release coating	Maximum use temperature	Weight	Colour
Release Ease® 234 TFP-HP	Fibreglass	PTFE	288°C	-	Brown
Release Ease® 234 TFP-1	Fibreglass	PTFE	288°C	-	Brown
Release Ease® 234 TFNP	Fibreglass	PTFE	288°C	-	Brown
Release Ease® 236 TFNP	Fibreglass	PTFE	288°C	-	Brown
Bagside and toolside breathing					
Dahltextx® SP-2	Nylon	-	177°C	140 g / m <sup>2</sup>	Light blue fabric side / White membrane side